

PBD 14 : 1994



PIAWAI BRUNEI DARUSSALAM
BRUNEI DARUSSALAM STANDARD

Specification for

**Ordinary and rapid-
hardening Portland cements**

MINISTRY OF DEVELOPMENT
NEGARA BRUNEI DARUSSALAM

Copyright Reserved

**Construction Planning and Research Unit
Ministry of Development
Old Airport, Jalan Berakas
Bandar Seri Begawan 1190
Negara Brunei Darussalam**

Specification for

**Ordinary and rapid-
hardening Portland cements**

PIAWAI BRUNEI DARUSSALAM

PBD 14 : 1994

First Edition

PBD 14 : 1994

Attention is drawn to the fact that this Brunei Darussalam Standards dos not confer any immunity from legal obligations in any contract for compliance to the Standard.

The Brunei Darussalam Standards are subject to periodical review according to the current needs of the local industries to keep abreast of progress in the industries concerned. Suggestions of amendments will be recorded and in due course brought to the notice of the committees concerned.

Amendments issued since publication

Amd No.	Date of issue	Text affected

CONTENTS

	Page
Foreword	7
Committee representation	9
 SPECIFICATION	
1. Scope	10
2. Composition and manufacture of Portland Cement	10
3. Chemical requirements	11
4. Physical requirements	12
5. Storage	13
6. Sampling	14
7. Facilities for sampling and identifying	14
8. Manufacturer's certificates	15
9. Compliance	15
10. Delivery	15
11. Marking	15

	Page
APPENDICES	
A. Propylene glycol content	16
B. Insoluble residue (ISO recommendation No. 680)	18
C. Determination of magnesia (MgO)	19
D. Determination of sulphuric anhydride (SO ₃)	21
E. Determination of total silica (SiO ₂) CMACZKOWSKI method	22
F. Determination of total lime (CaO)	24
G. Determination of iron oxide (Fe ₂ O ₃)	25
H. Determination of aluminium oxide (Al ₂ O ₃)	27
J. Determination of loss on ignition	27
K. Test for fineness by determination of specific surface method	28
L. Determination of soundness	46
M. Determination of standard consistence	48
N. Test for setting time	51
P. Test for compressive strength	54
Q. Product guidance	67

TABLES		Page
1.	Maximum total sulphur expressed as SO ₃ (%)	12
2.	Compressive strength of cements	13
K.1	Density of mercury, viscosity of air (n) and n at given temperatures	31
K.2	Mass of cement (in g) required to form a bed 25.00 mm in diameter and 10.00 mm deep having a porosity of 0.475 over density range 2800 kg/m ³ to 3290 kg/m ³	32
K.3	Mass of cement (in g) required to form a bed 25.40 mm in diameter and 10.00 mm deep having a porosity of 0.475 over density range 2800 kg/m ³ to 3290 kg/m ³	32
K.4	Values for porosity of cement bed	41
K.5	Time of air flow	44
N.1	Temperature and humidity conditions	52
P.1	Temperature and humidity conditions	57
P.2	Mixes for mortar cubes	57
P.3	Mixes for concrete cubes	63
P.4	Mass of individual fractions of sand	63

	Page
FIGURES	
K.1 Details of permeability cell	35
K.2 Typical permeability apparatus with manometer and flowmeter	36
K.3 Blaine air permeability apparatus	45
L.1 Apparatus for the 'Le Chatelier Test'	47
M.1 Vicat apparatus for determining standard consistence	50
N.1 Vicat apparatus for determining setting times	53
P.1 Typical concrete mixer with paddle	65
P.3 Typical vibration machine for compacting mortar cubes	66

FOREWORD

This Brunei Darussalam Standard having been drafted, and prepared under the direction of the Technical Committee on Concrete under the authority of the Standards Committee, Ministry of Development.

This standard was published with all specifications reviewed in accordance to the current needs of the local building industry, and in preparing this standard, references were made to the following:-

1. BS 12 : 1989 Specification for Portland cements.
2. BS 4027 : 1980 Specification for sulphate-resisting Portland cement.
3. PBD 13 : 1994 Methods of test for water for making concrete.
4. BS 146 Specification for Portland-blastfurnace cement.
5. BS 1014 Specification for pigments for Portland cement and Portland cement products.
6. BS 1370 Low heat Portland cement.
7. BS 6100 Glossary of building and civil engineering terms
Part 6 : Concrete and plaster
Section 6.1 : Binders
8. BS 4246 Specification for low heat Portland-blast furnace cement.
9. BS 6588 Specification for Portland pulverized-fuel ash cement.

PBD 14 : 1994

10. MS 522 : Part 1 : 1989
Specification for Portland cement
(Ordinary and rapid-hardening)
Part 1 : Standard specification
(First Revision)
11. BS 6610 : 1985
Specification for pozzolanic cement with
pulverised-fuel ash as pozzolana
12. BS 8110 : Part 1 : 1985
Structural use of concrete
Code of practice for design and construction.
13. BS 4550
Method of testing cement
Part 1 : Sampling
Part 2 : Chemical tests
Part 3 : Physical tests
Section 3.3 : Fineness tests
Section 3.4 : Strength tests
Section 3.5 : Determination of standard
consistence
Section 3.6 : Test for setting times
Section 3.7 : Soundness test
14. SS 26 : 1984
Specification for Portland Cement
(Ordinary and Rapid-Hardening)

COMMITTEE REPRESENTATION

The Technical Committee on Concrete was entrusted by the Ministry of Development for the preparation of this Brunei Darussalam Standard. The members of the Technical Committee are as follows:-

- | | |
|---------------------------------------|---|
| 1. Pg Hj Matusin Pg Hj Matasan | Ministry of Development |
| 2. Awg Hj Yusop Hj Ibrahim | Ministry of Development |
| 3. Dyg Masni Hj Mohsin | Ministry of Industry & Primary Resources |
| 4. Dr. A. Q. Malik | University of Brunei Darussalam |
| 5. Awg Karunatne | Pertubuhan Ukur Jurutera Arkitek (PUJA) |
| 6. Awg Chiong Siong Khai | TECA Sdn Bhd |
| 7. Awg Anthony Wong | Ove Arup |
| 8. Awg Moo Kwang Yin | Ministry of Defence |
| 9. Awg Nicholas Leong | Brunei Shell Petroleum |
| 10. Awg Abd Latif Ali | Maktab Teknik Sultan Saiful Rijal |
| 11. Awg Abd Hakim Hj Hanafiah | Housing Development Department |
| 12. Awg Amer Hamzah Hj Abd Karim | Public Works Department |
| 13. Dyg Suzana bte Hj Awg Adenan | Public Works Department |
| 14. Awangku Shariful PSI Pg Hj Ismail | Petroleum Unit, Prime Minister's Department |

Specification

1. SCOPE

This Brunei Darussalam Standard specifies the requirements for the composition, the manufacture, chemical and physical properties, storage, sampling and marking of the following types of Portland cement:

- (a) Ordinary Portland cement;
- (b) Rapid-hardening Portland cement

2. COMPOSITION AND MANUFACTURE OF PORTLAND CEMENT

2.1 To obtain cement

The cement, whether ordinary or rapid-hardening, shall be obtained by pulverizing clinker, consisting mostly of calcium silicates obtained by heating to partial fusion a predetermined and homogeneous mixture of materials containing principally lime (CaO) and silica (SiO₂) with a smaller proportion of alumina (Al₂ O₃) and iron oxide (Fe₂ O₃). (See item no. 610 2101 of BS 6100 : Section 6.1)

2.2 Cement content

The cement shall contain no other added materials except as follows:

- (a) Water or gypsum or anhydrite, or other derivatives for calcium sulphate, or any combination of these substances; the amount of addition to be such that the limits shown for sulphuric anhydride and loss on ignition shall not be exceeded;
- (b) Metallic iron from the grinding process which shall not be regarded as an addition; and
- (c) Propylene glycol in a proportion by mass that shall not exceed 0.10% as determined by the method in Appendix A;

2.3 Coloured Portland cement

Coloured Portland cements shall be deemed to comply with the requirements of this Brunei Darussalam Standard provided that: